SL-F04 Premium Solar Greyback Frontlit Banner

FEATURES

PA-coated, 1000x1000, 20x20 base fabric.

Greyback makes it full opacity and extremley strong.

Can be used as banners indoor and outdoor.

SPECIFICATIONS



 \triangleright

 \geq

SL-F04



Available Width
Up to 5M

Ink printability Solvent Eco-Solvent UV Latex

+44(0)161 765 3400 www.soyang.co.uk Speachless.... I can't believe the great insta deals this we

BANNER

APPLICATIONS

Indoor or Outdoor Banners Frontlit Roll-up Banners



For test sample please contact us at to sales@soyang.co.uk or visit our website at www.soyang.co.uk

			BANNER
SL- F04 Premium Solc	ır Greyback Frontlit Banne	r	
100% opacity, extrem	00, 20x20 base fabric. Aley strong. ers both indoors and outdoors. INK PRINTABILITY OF CONTUNE SOLVENT CONTUNE OF CONTUNE		Speac I can't the gre deals
PROPERTIES	TEST METHOD	METRIC	IMPERIAL
Total Weight Base Fabric	DIN EN ISO 2286-2, ASTM D751 DIN 60001, ASTM D7641	330gsm 100% Pol	1.08 oz per sq ft yester
Yarn Dtex	DIN EN ISO 2060, ASTM D1907	550 x 550 dtex	500 x 500 denier
Shielding Rate	ANSI PH2.19, ISO/2	100%	
Tensile Strength	DIN EN ISO 1421	1650x1500 N/5cm	189x171 lbs/inch
Tear Strength	DIN 53363	265 x 265N	189 x 171lbs
Flame Resistance	DIN 4102-1-B1, NFPA 701 Test1	DIN 4102-1-B1, NFPA 701 Test1	
Width	DIN EN ISO 3759, ASTM D751-2006	Up to 5m	197inch
	DIN LIN 150 37 37, ASTM D7 51-2000	001000	177 11011

NOTE: It is normal that the weight of most products will have an average fluctuation of 5%. All above information shall only used as a guide; buyers shall independently test and determine the products suitability. The mentioned data are average of test result and should not be used for the purpose of lawsuit or warranty.



For test sample please contact us at to sales@soyang.co.uk or visit our website at www.soyang.co.uk

+44(0)161 765 3400 www.soyang.co.uk