

# ST-117R PET Vista Display

Recycled Polyester Warp Knitted Display Fabric



## FEATURES

- ▶ 100% Recycled Polyester
- ▶ Dense structure makes it ideal for highly impactful visual graphics
- ▶ Truly wrinkle free, can recover quickly after folded, makes it easy for transportation
- ▶ Ideal for retail and exhibition sectors in textile tension frames etc.

## SPECIFICATIONS

- ▶ Item No.  
**ST-117R**
- ▶ Raw Material  
**Recycled Polyester**
- ▶ Available Width  
**Up to 3.2M**
- ▶ Ink printability  
**Dye-Sub Direct**  
**Dye-Sub Transfer**  
**UV & LATEX**



## APPLICATIONS

**Retail Backdrops**  
**Exhibitions Graphics**  
**Artistic Display Textiles**



**SOYANG**  
EUROPE

+44(0)161 765 3400  
[www.soyang.co.uk](http://www.soyang.co.uk)

For test sample please contact us at [sales@soyang.co.uk](mailto:sales@soyang.co.uk)  
or visit our website at [www.soyang.co.uk](http://www.soyang.co.uk)

# ST-117R PET Vista Display

## Recycled Polyester Warp Knitted Display Fabric

### DESCRIPTION

Special tight structure makes it with high opacity even at a much lighter weight compared with other display textile fabric. Truly wrinkle free, can recover quickly after folded, makes it easy for transportation.

#### FEATURES



PVC Free



Phthalate Free



Wrinkle Free

#### INK PRINTABILITY



DYE Paper



DYE Direct



Latex



UV



### PROPERTIES

### TEST METHOD

### METRIC

### IMPERIAL

PROPERTIES	TEST METHOD	METRIC	IMPERIAL
Total Weight	DIN EN ISO 2286-2, ASTM D751	210 g/sq.m	6.4oz/sq.yd
Base Fabric	DIN 60001-3	100% Recycled Polyester	
Weave Method	N/A	Warp-knitted	
Shrinkage	210°C, 1min	≤2%	
Shielding Rate	ANSI PH2.19, ISO 5/2	(56±4)%	
Bursting Strength	ASTMD378-2007 (2011)	963N	
Breaking Load	ISO 13934.1-2003	Warp 390N Weft 1200N	
Tearing Strength	ISO 13937.2 2000	Warp 22N Weft 36N	
Flame Resistance	DIN 4102-1-B1, NFPA 701, BS5867	Test1EN1350 B1 Type B	
Recommend Fixation	N/A	°C-190°C, 1-2min	
Yellowing Temperature	SUPRKC REX-C400	≤210°C	
Width Available	DIN EN ISO 3759, ASTM D751-2006	Max 320cm	126"
Standard Length	NA	50m	55yds

NOTE: It is normal that the weight of most products will have an average fluctuation of 5%. All above information shall only used as a guide; buyers shall independently test and determine the products suitability. The mentioned data are average of test result and should not be used for the purpose of lawsuit or warranty



**SOYANG**  
EUROPE

+44(0)161 765 3400  
[www.soyang.co.uk](http://www.soyang.co.uk)

For test sample please contact us at to [sales@soyang.co.uk](mailto:sales@soyang.co.uk)  
or visit our website at [www.soyang.co.uk](http://www.soyang.co.uk)